



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer
6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP733P

A film grade high density polyethylene

TYPICAL APPLICATIONS:

- Moisture sensitive packaging
- Food packaging
- Blends
- Co-extrusions
- Release liners

Features:

- Excellent MVTR
- Improved stiffness properties
- Improved scuff resistance
- Good processability
- Low gel levels
- FDA 21 CFR 177.1520 (c) 3.2a

Physical Properties	Typical Values*	Test Method(s)
Melt Index (Condition 190 °C/2.16 kg)	8.0 g/10 min	D-1238
Density	0.962 g/cm ³	D-1505
Vicat Softening Temperature	250 °F	D-1525

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.