



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer
6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP261

A 35 melt flow medium impact copolymer

TYPICAL APPLICATIONS:

- Housewares
- Dairy packaging
- Stadium cups

Features:

- FDA 21 CFR 177.1520

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	35.0 g/10 min	D-1238
Density	0.90 g/cm ³	D-792
Tensile Strength, Yield (50 mm/min)	3,350 psi	D-638
Elongation, Yield (50 mm/min)	7%	D-638
Flexural Modulus , 1% Secant, 1.3 mm/min	145,000 psi	D-790A
Notched Izod Impact Strength, 73 °F	2.5 ft-lb/in	D-256
Heat Deflection Temperature at 66 psi	88 °C	D-648
Rockwell Hardness	104 R	D-785

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.