



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer
6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP151T

A 20 melt flow homopolymer polypropylene

TYPICAL APPLICATIONS:

- Caps and closures
- Toys
- Housewares
- Opaque containers

Features:

- High stiffness
- Nucleated
- Excellent anti-static properties
- Fast cycle times

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	20.0 g/10 min	D-1238
Density (Method B)	0.902 sp gr 23/23 °C	D-792
Flexural Modulus, 1% Secant (0.05 in/min)	250,000 psi	D-790
Tensile Elongation, Yield (2 in/min)	7.5%	D-638
Tensile Strength, Yield (2 in/min)	5,500 psi	D-638
Notched Izod Impact Strength, 73 °F	0.6 ft-lb/in	D-256
Rockwell Hardness	90 R	D-785

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.