



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP553

A 25 melt index low density polyethylene

### TYPICAL APPLICATIONS:

- Housewares
- Personal care products
- Luggage handles

### Features:

- Good warpage resistance
- Good flexibility
- Excellent flow
- FDA 21 CFR 177.1520 (c) 2.2

Physical Properties	Typical Values*	Test Method(s)
Melt Index (Condition 190 °C/2.16 kg)	25.0 g/10 min	D-1238
Density	0.925 g/cm <sup>3</sup>	D-1505
Vicat Softening Temperature	197 °F	D-1525
Brittleness Temperature	-26 °F	D-746
Tensile Strength, Yield (2 in/min)	1,700 psi	D-638
Elongation, Break (2 in/min)	150%	D-638
Flexural Modulus, Tangent (0.5 in/min)	48,000 psi	D-790
Durometer Hardness, Shore D	51	D-2240

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.