



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP820

A high molecular weight high density polyethylene

### TYPICAL APPLICATIONS:

- Drums
- Small engine fuel tanks
- Automotive and portable fuel tanks
- Containers
- Compression molding
- Food packaging
- Large part blow molding
- Thermoformed parts
- Heavy gauge sheet

### Features:

- Superior stress crack resistance
- High impact strength
- Outstanding melt strength
- Excellent processability  
FDA approved

Physical Properties	Typical Values*	Test Method(s)
High Load Melt Index (190 °C/21.6kg)	5.5 g/10 min	D-1238
Melt Index (190 °C/C.16kg)	<0.10 g/10 min	D-1238
Density	0.946 g/cm <sup>3</sup>	D-4883
Brittleness Temperature	<-105 °F	D-746
Vicat Softening Temperature	261 °F	D-1525
Tensile Strength, Yield	3,480 psi	D-638
Tensile Elongation, Break	1,100%	D-638
Flexural Modulus, Tangent	149,000 psi	D-790
ESCR, Condition A (100% Igepal)	>1000 h	D-1693
Tensile Impact Strength (73 °F)	200 ft-lb/in <sup>2</sup>	D-1822

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.