



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP502

A fractional melt low density polyethylene

### TYPICAL APPLICATIONS:

- Agricultural film
- Blend partner
- Construction film
- Foams
- Heavy duty bags
- High performance collation shrink
- Pallet shrink film
- Profile extrusion

### Features:

- High strength properties
- Medium optical properties
- Slip: zero
- Anti-block: zero

Physical Properties	Typical Values*	Test Method(s)
Melt Index (190 °C/2.16 kg)	0.33 g/10 min	
Density	0.922 g/cm <sup>3</sup>	
Peak Melting Temperature	228 °F	
Film Properties	Typical Values*	Test Method(s)
Haze	11%	D-1003
Gloss 45°	54	D-2457
Elmendorf Tear Strength, MD TD	400 g 750 g	D-1922
Tensile Strength, Yield MD TD	1,740 psi 1,600 psi	D-882
Tensile Strength, Break MD TD	3,480 psi 3,190 psi	D-882
Tensile Modulus, 1% Secant MD TD	30,500 psi 34,800 psi	D-882
Elongation, Break MD TD	500% 650%	D-882
Dart Drop Impact	320 g	D-1709A

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.