



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer
6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP692QB

A hexane linear low density polyethylene

TYPICAL APPLICATIONS:

- Industrial liners
- Stretch wrap
- Garment and carrier bags
- General purpose packaging

Features:

- Good stiffness at thin gauges
- Excellent processing characteristics
- Processing aid: yes
- Slip: zero
- Anti-block: 7500 ppm

Physical Properties	Typical Values*	Test Method(s)
Melt Index, 190 °C/2.16 kg	0.9 g/10 min	D-1238
Density	0.918 g/cm ³	D-1505
Film Properties	Typical Values*	Test Method(s)
Haze	21%	D-1003
Gloss, 60°	70	D-2457
COF	0.5	D-1894
Dart	250g/mil	D-1709
Elmendorf Tear, MD. TD	400g/mil 700g/mil	D-1922
Tensile Strength, Break MD. TD	4300 psi 2900 psi	D-882
Tensile Modulus, 1% Secant MD TD	30000 psi 33000 psi	D-882
Elongation, Break MD TD	400% 600%	D-882

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.