



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP111

A low melt flow homopolymer polypropylene

### TYPICAL APPLICATIONS:

- Strapping
- Profiles

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16kg)	1.3 g/10 min	D-1238
Flexural Modulus (0.05 in/min, 1% Secant)	185,000 psi	D-790A
Tensile Strength, Yield (2 in/min)	4,800 psi	D-638
Tensile Elongation, Yield (2 in/min)	11%	D-638
Notched Izod Impact Strength, 23 °C	0.5 ft-lbs/in	D-256A
Rockwell Hardness	101 R	D-785

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.