



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer
6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP121W

A 4.0 melt flow homopolymer polypropylene

TYPICAL APPLICATIONS:

- Raffia applications

Features:

- Low water carryover
- FDA 21 CFR 177.1520

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate, I ₂ @ 230 °C	4.0 g/10 min	D-1238
Density	0.90 g/cm ³	D-1505
Flexural Modulus (1.3 mm/min), 1% Secant	180,000 psi	D-790
Tensile Strength, Yield (50 mm/min)	4,800 psi	D-638
Tensile Elongation, Yield (50 mm/min)	9%	D-638
Notched Izod Impact Strength @ 73 °F	0.8 ft-lb/in	D-256
Rockwell Hardness	105 R	D-785

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.