



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP702Z

A blow molding grade high density polyethylene

### TYPICAL APPLICATIONS:

- Injection blow molding

### Features:

- Zinc stearate
- Excellent stiffness
- Exceptional processability  
FDA 21 CFR 177.1520 (c) 3.1 & 3.2a

Physical Properties	Typical Values*	Test Method(s)
Melt Index (190 °C/2.16 kg)	0.35 g/10 min	D-1238
Density	0.955 g/cm <sup>3</sup>	D-1505
Tensile Strength, Yield (2 in/min)	4,000 psi	D-638
Tensile Elongation, Break (2 in/min)	600%	D-638
Flexural Modulus, Tangent	210,000 psi	D-790
ESCR, Condition B (100% Igepal), F <sub>50</sub>	35 h	D-1693
Brittleness Temperature	<-103 °F	D-746

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.