



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP121W

A 4.0 melt flow homopolymer polypropylene

### TYPICAL APPLICATIONS:

- Raffia applications

### Features:

- Low water carryover
- FDA 21 CFR 177.1520

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate, I <sub>2</sub> @ 230 °C	4.0 g/10 min	D-1238
Density	0.90 g/cm <sup>3</sup>	D-1505
Flexural Modulus (1.3 mm/min), 1% Secant	180,000 psi	D-790
Tensile Strength, Yield (50 mm/min)	4,800 psi	D-638
Tensile Elongation, Yield (50 mm/min)	9%	D-638
Notched Izod Impact Strength @ 73 °F	0.8 ft-lb/in	D-256
Rockwell Hardness	105 R	D-785

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.