



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer

6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP261T

A 35 melt flow medium impact copolymer

TYPICAL APPLICATIONS:

- Injection molded caps and closures
- Housewares
- Opaque containers

Features:

- Nucleation and anti-stat
- High gloss
- Good impact resistance and stiffness
- Low warpage
- Fast cycle times
- FDA compliant

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16kg)	35.0 g/10 min	D-1238
Density	0.902 sp gr 23/23 °C	D-792
Tensile Strength, Yield (2 in/min)	4,500 psi	D-638
Elongation, Yield	7%	D-638
Flexural Modulus (0.05 in/min, 1% Secant)	215,000 psi	D-790
Notched Izod Impact Strength, 73 °F	1.0 ft-lb/in	D-256
DTUL at 66 psi – Unannealed	116 °C	D-648

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.