



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer
6190 Powers Ferry Road, N.W.
Suite 290
Atlanta, GA 30339
Phone (770) 916-0607
Fax (770) 916-0608
www.southernpolymer.com

WPP151F

An 18 melt homopolymer polypropylene

TYPICAL APPLICATIONS:

- Staple fiber
- BCF
- Filament yarn
- Geotextile and agriculture
- Injection molding

Features:

- Superior processing stability
- Anti gas-fade stabilization
- Good tear strength

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	18.0 g/10 min	D-1238
Density (Method B)	0.902 s gr 23/23°C	D-792
Tensile Strength, Yield (2 in/min)	5,000 psi	D-638
Tensile Elongation, Yield (2 in/min)	9%	D-638

* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.