



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer  
6190 Powers Ferry Road, N.W.  
Suite 290  
Atlanta, GA 30339  
Phone (770) 916-0607  
Fax (770) 916-0608  
www.southernpolymer.com

## WPP673-01

A 50 melt index butane linear low density polyethylene

### TYPICAL APPLICATIONS:

- Freezer lids
- Housewares
- Closures and dispensers
- Protective caps

### Features:

- Excellent toughness
- Excellent tear resistance

Physical Properties	Typical Values*	Test Method(s)
Melt Index (190 °C/2.16)	50.0 g/10 min	D-1238
Density	0.926 g/cm <sup>3</sup>	D-4883
Tensile Strength, Yield	1,650 psi	D-638
Tensile Elongation, Break	90%	D-638
Flexural Modulus, 1% Secant	39,200 psi	D-790B
ESCR (Condition B, F50, 10% Igepal)	<1.00 hr	D-1693B
Vicat Softening Point	197 °F	D-1525
Melting Temperature	253 °F	D-3418

\* Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Southern Polymer representative.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.